

NAO .C-01

NAO 1.60 JARDIN C-01 BEIG



← 27 inch. simulation 70 cm. simulación →

REPEAT WEFT REPETICIÓN TRAMA:
REPEAT WARP REPETICIÓN URDIMBRE:

TECHNICAL SHEET / CARACTERÍSTICAS TÉCNICAS

WIDTH (inches) / ANCHO (cm)	63 / 160	
HS CODE / PARTIDA ARANCELARIA	55152190	
ROLL LENGTH (yd) / TAMAÑO PIEZA (mts)	38.5 / 35	
COMPOSITION / COMPOSICION	100% ACRILICO/100%ACRYLIC	
WEIGHT (oz/yd2) / PESO (gr/m2) (+/-5%)	5.59 / 190	
WEIGHT (oz/yd) / PESO (gr/ml)	9.80 / 304.00	
ABRASION RESISTANCE (CYCLES) / RESISTENCIA A LA ABRASIÓN (ciclos)	20000	UNE EN ISO 12947-2
PILLING RESISTANCE (degrees) (1-5) / RESISTENCIA AL PILLING (grados) (1-5)	4-5	UNE EN ISO 12945-2
COLOUR FASTNESS TO LIGHT (degrees) (1-8) / SOLIDEZ A LA LUZ (grados) (1-8)	5-6	UNE EN ISO 105-B02
COLOUR FASTNESS TO RUBBING (degrees) (1-5) / SOLIDEZ AL FROTE (grados)	4-5	UNE EN ISO 105-X12
COLOUR FASTNESS TO WASH (degrees) (1-5) / SOLIDEZ AL LAVADO (grados)	5	UNE EN ISO 105-C06
(%) WARP SHRINKAGE / ENCOGIMIENTO URDIMBRE (%)	0.0	UNE EN ISO 5077.
(%) WEFT SHRINKAGE / ENCOGIMIENTO TRAMA (%)	2.5	UNE EN ISO 5077
WARP SEAM SLIPPAGE (mm) / DESLIZAMIENTO DE LA COSTURA URDIMBRE (mm)	3.60	UNE EN ISO 13936-1
WEFT SEAM SLIPPAGE (mm) / DESLIZAMIENTO DE LA COSTURA TRAMA (mm)	3.40	UNE EN ISO 13936-1
WATER PENETRATION RESISTANCE. TEST UNDER PRESSURE (WATER COLUMN)	11	UNE EN ISO 20811:1993
RESISTANT / RESISTENTES	TEFLON STAIN RESISTANT / ANTIMANCHAS TEFLÓN	