



PERPIÑAN 82

PERPIÑAN 2,80 NIZA COL.82



**FIRE
RETARDANT**
EN 1021-1:2014
NFPA 260
CAL TB 117
BS 5852-1



REPEAT WEFT REPETICIÓN TRAMA: 14 inches - 35.5 cm
REPEAT WARP REPETICIÓN URDIMBRE: 20 inches - 51.5 cm

TECHNICAL SHEET / CARACTERÍSTICAS TÉCNICAS

HS CODE / PARTIDA ARANCELARIA	110 / 280	
ROLL LENGTH (yd) / TAMAÑO PIEZA (mts)	52114910	
COMPOSITION / COMPOSICION	27.5 / 25	
WEIGHT (oz/yd ²) / PESO (gr/m ²) (+/-5%)	CO35% PAN35% PES30%	
WEIGHT (oz/yd) / PESO (gr/ml)	11.63 / 395	
ABRASION RESISTANCE (CYCLES) / RESISTENCIA A LA ABRASIÓN (ciclos)	35.67 / 1106.00	
PILLING RESISTANCE (degrees) (1-5) / RESISTENCIA AL PILLING (grados) (1-5)	12000	UNE EN ISO 12947-2
COLOUR FASTNESS TO LIGHT (degrees) (1-8) / SOLIDEZ A LA LUZ (grados) (1-8)	4	UNE EN ISO 12945-2
COLOUR FASTNESS TO RUBBING (degrees) (1-5) / SOLIDEZ AL FROTE (grados)	4-5	UNE EN ISO 105-B02
COLOUR FASTNESS TO WASH (degrees) (1-5) / SOLIDEZ AL LAVADO (grados)	4-5	UNE EN ISO 105-X12
(%) WARP SHRINKAGE / ENCOGIMIENTO URDIMBRE (%)	4-5	UNE EN ISO 105-C06
(%) WEFT SHRINKAGE / ENCOGIMIENTO TRAMA (%)	1	UNE EN ISO 5077.
FIRE RETARDANT RULE / IGNÍFUGOS UNE EN 1021:2014-1	2	UNE EN ISO 5077
FIRE RETARDANT RULE / IGNÍFUGOS BS 5852-1	PASA	UNE EN 1021:2014-1
	PASA	BS 5852-1