




REPEAT WEFT REPETICIÓN TRAMA: 9 inches - 23.5 cm  
REPEAT WARP REPETICIÓN URDIMBRE: 27 inches - 68 cm

## MANGLAR 13

### MANGLAR 2,80 ARENA COL.13



## TECHNICAL SHEET / CARACTERÍSTICAS TÉCNICAS

|                                                                                |                                  |                    |
|--------------------------------------------------------------------------------|----------------------------------|--------------------|
| WIDTH (inches) / ANCHO (cm)                                                    | 110 / 280                        |                    |
| HS CODE / PARTIDA ARANCELARIA                                                  | 52115100                         |                    |
| ROLL LENGTH (yd) / TAMAÑO PIEZA (mts)                                          | 33.0 / 30                        |                    |
| COMPOSITION / COMPOSICION                                                      | CO75% PES25%                     |                    |
| WEIGHT (oz/yd2) / PESO (gr/m2) (+/-5%)                                         | 7.21 / 245                       |                    |
| WEIGHT (oz/yd) / PESO (gr/ml)                                                  | 22.12 / 686.00                   |                    |
| ABRASION RESISTANCE (CYCLES) / RESISTENCIA A LA ABRASIÓN ( ciclos )            | 30000                            | UNE EN ISO 12947-2 |
| PILLING RESISTANCE ( degrees ) (1-5) / RESISTENCIA AL PILLING ( grados ) (1-5) | 4                                | UNE EN ISO 12945-2 |
| COLOUR FASTNESS TO LIGHT ( degrees ) (1-8) / SOLIDEZ A LA LUZ ( grados ) (1-8) | 6                                | UNE EN ISO 105-B02 |
| COLOUR FASTNESS TO RUBBING ( degrees ) (1-5) / SOLIDEZ AL FROTE ( grados )     | 4                                | UNE EN ISO 105-X12 |
| COLOUR FASTNESS TO WASH ( degrees ) (1-5) / SOLIDEZ AL LAVADO ( grados )       | 4                                | UNE EN ISO 105-C06 |
| (%) WARP SHRINKAGE / ENCOGIMIENTO URDIMBRE ( % )                               | 3.5                              | UNE EN ISO 5077.   |
| (%) WEFT SHRINKAGE / ENCOGIMIENTO TRAMA (%)                                    | 4                                | UNE EN ISO 5077    |
| WARP TENSILE STRENGTH (N) / RESISTENCIA A LA TRACCIÓN URDIMBRE (N)             | 446.11                           | UNE EN ISO 13934-1 |
| WEFT TENSILE STRENGTH (N) / RESISTENCIA A LA TRACCIÓN TRAMA (N)                | 486.75                           | UNE EN ISO 13934-1 |
| WARP EXTENSION AT BREAK (mm) / ALARGAMIENTO HASTA LA ROTURA                    | 63.85                            | UNE EN ISO 13934-1 |
| WEFT EXTENSION AT BREAK (mm) / ALARGAMIENTO HASTA LA ROTURA TRAMA              | 16.9                             | UNE EN ISO 13934-1 |
| WARP TEARING STRENGTH ( N ) / RESISTENCIA AL RASGADO URDIMBRE ( N )            | 63.2                             | UNE EN ISO 13937-3 |
| WEFT TEARING STRENGTH (N) / RESISTENCIA AL RASGADO TRAMA (N)                   | 32.58                            | UNE EN ISO 13937-3 |
|                                                                                | 3.25                             | UNE EN ISO 13936-1 |
| WEFT SEAM SLIPPAGE (mm) / DESLIZAMIENTO DE LA COSTURA TRAMA ( mm )             | 3.15                             | UNE EN ISO 13936-1 |
| FIRE RETARDANT RULE / IGNÍFUGOS UNE EN 1021:2014-1                             | PASA                             | UNE EN 1021:2014-1 |
| FIRE RETARDANT RULE / IGNÍFUGOS BS 5852-1                                      | PASA                             | BS 5852-1          |
| RESISTANT / RESISTENTES                                                        | STAIN RESISTANT /<br>ANTIMANCHAS |                    |