



## FANDANGO 36

### FANDANGO 1.40 VANIA COL.36



REPEAT WEFT REPETICIÓN TRAMA: 9 inches - 24 cm  
REPEAT WARP REPETICIÓN URDIMBRE: 5 inches - 12 cm

## TECHNICAL SHEET / CARACTERÍSTICAS TÉCNICAS

WIDTH (inches) / ANCHO (cm)	55 - 110 / 140 - 280
HS CODE / PARTIDA ARANCELARIA	52115100
ROLL LENGTH (yd) / TAMAÑO PIEZA (mts)	27.5 / 25
COMPOSITION / COMPOSICIÓN	PES55% CO45%
WEIGHT (oz/yd <sup>2</sup> ) / PESO (gr/m <sup>2</sup> ) (+-5%)	9.12 / 310
WEIGHT (oz/yd) / PESO (gr/ml)	14.00 - 27.99 / 434.00 - 868.00
ABRASION RESISTANCE (CYCLES) / RESISTENCIA A LA ABRASIÓN ( ciclos )	>40000
PILLING RESISTANCE ( degrees ) (1-5) / RESISTENCIA AL PILLING ( grados ) (1-5)	5
COLOUR FASTNESS TO LIGHT ( degrees ) (1-8) / SOLIDEZ A LA LUZ ( grados ) (1-8)	5
COLOUR FASTNESS TO RUBBING ( degrees ) (1-5) / SOLIDEZ AL FROTE ( grados )	5
COLOUR FASTNESS TO WASH ( degrees ) (1-5) / SOLIDEZ AL LAVADO ( grados )	5
(%) WARP SHRINKAGE / ENCOGIMIENTO URDIMBRE ( % )	2
(%) WEFT SHRINKAGE / ENCOGIMIENTO TRAMA ( % )	3
WARP TENSILE STRENGTH (N) / RESISTENCIA A LA TRACCIÓN URDIMBRE (N)	1500
WEFT TENSILE STRENGTH (N) / RESISTENCIA A LA TRACCIÓN TRAMA (N)	541.39
WARP EXTENSION AT BREAK (mm) / ALARGAMIENTO HASTA LA ROTURA	68.9
WEFT EXTENSION AT BREAK (mm) / ALARGAMIENTO HASTA LA ROTURA TRAMA	22.3
WARP TEARING STRENGTH (N) / RESISTENCIA AL RASGADO URDIMBRE (N)	>150
WEFT TEARING STRENGTH (N) / RESISTENCIA AL RASGADO TRAMA (N)	105.09
WARP SEAM SLIPPAGE (mm) / DESLIZAMIENTO DE LA COSTURA URDIMBRE (mm)	2.9
WEFT SEAM SLIPPAGE (mm) / DESLIZAMIENTO DE LA COSTURA TRAMA ( mm )	3.6
FIRE RETARDANT RULE / IGNÍFUGOS UNE EN 1021:2014-1	PASA
FIRE RETARDANT RULE / IGNÍFUGOS BS 5852-1	BS 5852-1