


PANTERA 17

PANTERA 1,50 MICRO EST. COL.17



← 27 inch. simulation →
70 cm. simulación

REPEAT WEFT REPETICIÓN TRAMA: 29 inches - 72.5 cm
REPEAT WARP REPETICIÓN URDIMBRE: 18 inches - 45.5 cm

TECHNICAL SHEET / CARACTERÍSTICAS TÉCNICAS

WIDTH (inches) / ANCHO (cm)	59 / 150	
HS CODE / PARTIDA ARANCELARIA		
ROLL LENGTH (yd) / TAMAÑO PIEZA (mts)	33.0 / 30	
COMPOSITION / COMPOSICION	PESmicro50% CO50%	
WEIGHT (oz/yd2) / PESO (gr/m2) (+/-5%)	8.24 / 280	
WEIGHT (oz/yd) / PESO (gr/ml)	13.55 / 420.00	
ABRASION RESISTANCE (CYCLES) / RESISTENCIA A LA ABRASIÓN (ciclos)	30000	UNE EN ISO 12947-2
PILLING RESISTANCE (degrees) (1-5) / RESISTENCIA AL PILLING (grados) (1-5)	4-5	UNE EN ISO 12945-2
COLOUR FASTNESS TO LIGHT (degrees) (1-8) / SOLIDEZ A LA LUZ (grados) (1-8)	5	UNE EN ISO 105-B02
COLOUR FASTNESS TO RUBBING (degrees) (1-5) / SOLIDEZ AL FROTE (grados)	4	UNE EN ISO 105-X12
COLOUR FASTNESS TO WASH (degrees) (1-5) / SOLIDEZ AL LAVADO (grados)	4-5	UNE EN ISO 105-C06
(%) WARP SHRINKAGE / ENCOGIMIENTO URDIMBRE (%)	3	UNE EN ISO 5077.
(%) WEFT SHRINKAGE / ENCOGIMIENTO TRAMA (%)	2.5	UNE EN ISO 5077