




CESAR 90

CESAR 2,80 EPIC COL.90



UPHOLSTERY
Tapicería



**FIRE
RETARDANT**
EN 1021-1:2014
NFPA 260
CAL TB 117
BS 5852-1



REPEAT WEFT REPETICIÓN TRAMA: 7 inches - 17.7 cm
REPEAT WARP REPETICIÓN URDIMBRE: 9 inches - 22 cm

TECHNICAL SHEET / CARACTERÍSTICAS TÉCNICAS

WIDTH (inches) / ANCHO (cm)	110 - 55 / 280 - 140	
HS CODE / PARTIDA ARANCELARIA	54078300	
ROLL LENGTH (yd) / TAMAÑO PIEZA (mts)	27.5 / 25	
COMPOSITION / COMPOSICION	PES40% PAN30% CO30%	
WEIGHT (oz/yd2) / PESO (gr/m2) (+/-5%)	10.30 / 350	
WEIGHT (oz/yd) / PESO (gr/ml)	31.61 - 15.80 / 980.00 - 490.00	
ABRASION RESISTANCE (CYCLES) / RESISTENCIA A LA ABRASIÓN (ciclos)	20000	UNE EN ISO 12947-2
PILLING RESISTANCE (degrees) (1-5) / RESISTENCIA AL PILLING (grados) (1-5)	5	UNE EN ISO 12945-2
COLOUR FASTNESS TO LIGHT (degrees) (1-8) / SOLIDEZ A LA LUZ (grados) (1-8)	5	UNE EN ISO 105-B02
COLOUR FASTNESS TO RUBBING (degrees) (1-5) / SOLIDEZ AL FROTE (grados)	5	UNE EN ISO 105-X12
(%) WARP SHRINKAGE / ENCOGIMIENTO URDIMBRE (%)	2.5	UNE EN ISO 105-C06
(%) WEFT SHRINKAGE / ENCOGIMIENTO TRAMA (%)	4.8	UNE EN ISO 5077.
WARP TENSILE STRENGTH (N) / RESISTENCIA A LA TRACCIÓN URDIMBRE (N)	1372.47	UNE EN ISO 5077
WEFT TENSILE STRENGTH (N) / RESISTENCIA A LA TRACCIÓN TRAMA (N)	1008.64	UNE EN ISO 13934-1
WARP EXTENSION AT BREAK (mm) / ALARGAMIENTO HASTA LA ROTURA	85.55	UNE EN ISO 13934-1
WEFT EXTENSION AT BREAK (mm) / ALARGAMIENTO HASTA LA ROTURA TRAMA	16.55	UNE EN ISO 13934-1
WARP SEAM SLIPPAGE (mm) / DESLIZAMIENTO DE LA COSTURA URDIMBRE (mm)		UNE EN ISO 13936-1
WEFT SEAM SLIPPAGE (mm) / DESLIZAMIENTO DE LA COSTURA TRAMA (mm)	3	UNE EN ISO 13936-1
FIRE RETARDANT RULE / IGNÍFUGOS UNE EN 1021:2014-1	PASA	UNE EN 1021:2014-1
FIRE RETARDANT RULE / IGNÍFUGOS BS 5852-1	PASA	BS 5852-1