



REPEAT WEFT REPETICIÓN TRAMA: 11 inches - 28 cm
REPEAT WARP REPETICIÓN URDIMBRE: 11 inches - 27 cm

BORGES 63

BORGES 2.80 VANIA COL.63



UPHOLSTERY
Tapicería



CUSHIONS
Cojines



**FIRE
RETARDANT**
EN 1021-1:2014
NFPA 260
CAL TB 117
BS 5852-1



**CONFIDENCE
IN TEXTILES**
Tested for harmful substances
according to Oeko-Tex® Standard 100
981699 AITEX

TECHNICAL SHEET / CARACTERÍSTICAS TÉCNICAS

HS CODE / PARTIDA ARANCELARIA	110 - 55 / 280 - 140	
ROLL LENGTH (yd) / TAMAÑO PIEZA (mts)	52115100	
COMPOSITION / COMPOSICION	27.5 / 25	
WEIGHT (oz/yd2) / PESO (gr/m2) (+/-5%)	PES55% CO45%	
WEIGHT (oz/yd) / PESO (gr/ml)	9.12 / 310	
ABRASION RESISTANCE (CYCLES) / RESISTENCIA A LA ABRASIÓN (ciclos)	27.99 - 14.00 / 868.00 - 434.00	
PILLING RESISTANCE (degrees) (1-5) / RESISTENCIA AL PILLING (grados) (1-5)	>40000	UNE EN ISO 12947-2
VELCRO EFFECT (1-5) / EFECTO VELCRO (1-5)	5	UNE EN ISO 12945-2
COLOUR FASTNESS TO LIGHT (degrees) (1-8) / SOLIDEZ A LA LUZ (grados) (1-8)	5	CS4946
COLOUR FASTNESS TO RUBBING (degrees) (1-5) / SOLIDEZ AL FROTE (grados)	5	UNE EN ISO 105-B02
COLOUR FASTNESS TO WASH (degrees) (1-5) / SOLIDEZ AL LAVADO (grados)	5	UNE EN ISO 105-X12
(%) WARP SHRINKAGE / ENCOGIMIENTO URDIMBRE (%)	2	UNE EN ISO 105-C06
(%) WEFT SHRINKAGE / ENCOGIMIENTO TRAMA (%)	3	UNE EN ISO 5077.
WEFT TENSILE STRENGTH (N) / RESISTENCIA A LA TRACCIÓN TRAMA (N)	1500	UNE EN ISO 5077
WARP EXTENSION AT BREAK (mm) / ALARGAMIENTO HASTA LA ROTURA	541.39	UNE EN ISO 13934-1
WEFT EXTENSION AT BREAK (mm) / ALARGAMIENTO HASTA LA ROTURA TRAMA	68.9	UNE EN ISO 13934-1
WARP TEARING STRENGTH (N) / RESISTENCIA AL RASGADO URDIMBRE (N)	22.3	UNE EN ISO 13934-1
WEFT TEARING STRENGTH (N) / RESISTENCIA AL RASGADO TRAMA (N)	>150	UNE EN ISO 13937-3
WARP SEAM SLIPPAGE (mm) / DESLIZAMIENTO DE LA COSTURA URDIMBRE (mm)	105.09	UNE EN ISO 13937-3
WEFT SEAM SLIPPAGE (mm) / DESLIZAMIENTO DE LA COSTURA TRAMA (mm)	2.9	UNE EN ISO 13936-1
FIRE RETARDANT RULE / IGNÍFUGOS UNE EN 1021:2014-1	3.6	UNE EN ISO 13936-1
FIRE RETARDANT RULE / IGNÍFUGOS BS 5852-1	PASA	UNE EN 1021:2014-1
	PASA	BS 5852-1