


← 27 inch. simulation →
70 cm. simulación

PIERO 90

PIERO 2.80 HYDRA COL.90



UPHOLSTERY
Tapicería



CUSHIONS
Cojines



CONFIDENCE
IN TEXTILES
Tested for harmful substances
according to Oeko-tex® Standard 100
981699
ATTEX

REPEAT WEFT REPETICIÓN TRAMA: 2 inches - 3.5 cm
REPEAT WARP REPETICIÓN URDIMBRE: 1 inches - 3 cm

TECHNICAL SHEET / CARACTERÍSTICAS TÉCNICAS

WIDTH (inches) / ANCHO (cm)	110 - 55 / 280 - 140
HS CODE / PARTIDA ARANCELARIA	52115100
ROLL LENGTH (yd)	27.5 / 25
WEIGHT (oz/yd ²) / PESO (gr/m ²) (+-5%)	PES65% CO35%
WEIGHT (oz/yd) / PESO (gr/ml)	6.48 / 220
ABRASION RESISTANCE (CYCLES) / RESISTENCIA A LA ABRASIÓN (ciclos)	>40000
PILLING RESISTANCE (degrees) (1-5) / RESISTENCIA AL PILLING (grados) (1-5)	5
VELCRO EFFECT (1-5) / EFECTO VELCRO (1-5)	5
COLOUR FASTNESS TO LIGHT (degrees) (1-8) / SOLIDEZ A LA LUZ (grados) (1-8)	5
COLOUR FASTNESS TO RUBBING (degrees) (1-5) / SOLIDEZ AL FROTE (grados)	5
COLOUR FASTNESS TO WASH (degrees) (1-5) / SOLIDEZ AL LAVADO (grados)	5
(%) WARP SHRINKAGE / ENCOGIMIENTO URDIMBRE (%)	2.8
(%) WEFT SHRINKAGE / ENCOGIMIENTO TRAMA (%)	1
WARP TENSILE STRENGTH (N) / RESISTENCIA A LA TRACCIÓN URDIMBRE (N)	946.24
	438.85
WARP EXTENSION AT BREAK (mm) / ALARGAMIENTO HASTA LA ROTURA	64.4
WEFT EXTENSION AT BREAK (mm) / ALARGAMIENTO HASTA LA ROTURA TRAMA	20.6
WARP TEARING STRENGTH (N) / RESISTENCIA AL RASGADO URDIMBRE (N)	>150
WEFT TEARING STRENGTH (N) / RESISTENCIA AL RASGADO TRAMA (N)	31.8
	3.8
WEFT SEAM SLIPPAGE (mm)	3
FIRE RETARDANT RULE / IGNÍFUGOS UNE EN 1021:2014-1	PASA
	PASA
	BS 5852-1