



REPEAT WARP REPETICIÓN URDIMBRE: ----

WIDTH (inches) / ANCHO (cm)

**DENIS 90** DENIS 2,80 ANAIS COL.90



















110 / 280





## TECHNICAL SHEET / CARACTERÍSTICAS TÉCNICAS

WIDTH (Inches) / Arterio (cm)	110 / 200	
HS CODE / PARTIDA ARANCELARIA	52114910	
ROLL LENGTH (yd) / TAMAÑO PIEZA (mts)	33.0 / 30	
COMPOSITION / COMPOSICION	CO50% PES30% PAN20%	
WEIGHT (oz/yd2) / PESO (gr/m2) (+-5%)	8.83 / 300	
WEIGHT (oz/yd) / PESO (gr/ml)	<b>27.09</b> / 840.00	
ABRASION RESISTANCE (CYCLES) / RESISTENCIA A LA ABRASIÓN ( ciclos )	15000	UNE EN ISO 12947-2
PILLING RESISTANCE ( degrees ) (1-5) / RESISTENCIA AL PILLING ( grados ) (1-5)	4-5	UNE EN ISO 12945-2
VELCRO EFFECT (1-5) / EFECTO VELCRO (1-5)	5	CS4946
$ \hbox{COLOUR FASTNESS TO LIGHT ( degrees ) (1-8) } \hspace{0.2cm} / \hspace{0.1cm} \hbox{SOLIDEZ A LA LUZ ( grados ) (1-8)} $	5	UNE EN ISO 105-B02
COLOUR FASTNESS TO RUBBING ( degrees ) (1-5) / SOLIDEZ AL FROTE ( grados )	5	UNE EN ISO 105-X12
COLOUR FASTNESS TO WASH ( degrees ) (1-5) / SOLIDEZ AL LAVADO ( grados )	5	UNE EN ISO 105-C06
(%) WARP SHRINKAGE / ENCOGIMIENTO URDIMBRE ( % )	3	UNE EN ISO 5077.
(%) WEFT SHRINKAGE / ENCOGIMIENTO TRAMA (%)	2	UNE EN ISO 5077
WARP TENSILE STRENGTH (N) / RESISTENCIA A LA TRACCIÓN URDIMBRE (N)	1121	UNE EN ISO 13934-1
WEFT TENSILE STRENGTH (N) / RESISTENCIA A LA TRACCIÓN TRAMA (N)	825.05	UNE EN ISO 13934-1
WARP EXTENSION AT BREAK (mm) / ALARGAMIENTO HASTA LA ROTURA	92.65	UNE EN ISO 13934-1
WEFT EXTENSION AT BREAK (mm) / ALARGAMIENTO HASTA LA ROTURA TRAMA	24.8	UNE EN ISO 13934-1
WARP TEARING STRENGTH ( N ) / RESISTENCIA AL RASGADO URDIMBRE ( N )	48.77	UNE EN ISO 13937-3
WEFT TEARING STRENGTH (N) / RESISTENCIA AL RASGADO TRAMA (N)	33.83	UNE EN ISO 13937-3
WARP SEAM SLIPPAGE (mm) / DESLIZAMIENTO DE LA COSTURA URDIMBRE (mm)	1.4	UNE EN ISO 13936-1
WEFT SEAM SLIPPAGE (mm) / DESLIZAMIENTO DE LA COSTURA TRAMA ( mm )	1.6	UNE EN ISO 13936-1
FIRE RETARDANT RULE / IGNÍFUGOS UNE EN 1021:2014-1	PASA	UNE EN 1021:2014-1
FIRE RETARDANT RULE / IGNÍFUGOS BS 5852-1	PASA	BS 5852-1