



# COSMODARK 02

## COSMODARK 3.10 ULTRADARK 02



**FIRE  
RETARDANT**  
EN 13773:2003  
NFPA 701  
BS 5867-2



**BLACK OUT**  
Ocultante



**ULTRA  
DARK**  
solids



← 27 inch. simulation →  
← 70 cm. simulación →

REPEAT WEFT REPETICIÓN TRAMA:  
REPEAT WARP REPETICIÓN URDIMBRE:

### TECHNICAL SHEET / CARACTERÍSTICAS TÉCNICAS

	122 / 310	
HS CODE / PARTIDA ARANCELARIA		
ROLL LENGTH (yd) / TAMAÑO PIEZA (mts)	33.0 / 30	
COMPOSITION / COMPOSICION	PES FR 100%	
WEIGHT (oz/yd <sup>2</sup> ) / PESO (gr/m <sup>2</sup> ) (+-5%)	15.13 / 514	
WEIGHT (oz/yd) / PESO (gr/ml)	51.39 / 1593.40	
COLOUR FASTNESS TO LIGHT ( degrees ) (1-8) / SOLIDEZ A LA LUZ ( grados ) (1-8)	5	UNE EN ISO 105-B02
COLOUR FASTNESS TO WASH ( degrees ) (1-5) / SOLIDEZ AL LAVADO ( grados )	5	UNE EN ISO 105-C06
(%) WARP SHRINKAGE / ENCOGIMIENTO URDIMBRE ( % )	1.2	UNE EN ISO 5077.
(%) WEFT SHRINKAGE / ENCOGIMIENTO TRAMA ( % )	0.4	UNE EN ISO 5077
WARP SEAM SLIPPAGE (mm) / DESLIZAMIENTO DE LA COSTURA URDIMBRE (mm)	0.3	UNE EN ISO 13936-1
WEFT SEAM SLIPPAGE (mm) / DESLIZAMIENTO DE LA COSTURA TRAMA ( mm )	0.3	UNE EN ISO 13936-1
FIRE RETARDANT RULE / IGNÍFUGOS UNE EN 13773:2003	C1	UNE EN 13773:2003
OPACITY 100000 LUX / OPACIDAD 100000 LUX	0.02	CS1451LUX