




## CLOUD 04

### CLOUD 2,80 HOME COL.04



← 27 inch. simulation →  
← 70 cm. simulación →

REPEAT WEFT REPETICIÓN TRAMA: 1 inches - 2.8 cm  
REPEAT WARP REPETICIÓN URDIMBRE: 1 inches - 1.5 cm

## TECHNICAL SHEET / CARACTERÍSTICAS TÉCNICAS

|                                                                                |                                 |                    |
|--------------------------------------------------------------------------------|---------------------------------|--------------------|
| WIDTH (inches) / ANCHO (cm)                                                    | 110 - 55 / 280 - 140            |                    |
| HS CODE / PARTIDA ARANCELARIA                                                  | 54078300                        |                    |
| ROLL LENGTH (yd) / TAMAÑO PIEZA (mts)                                          | 33.0 / 30                       |                    |
| COMPOSITION / COMPOSICION                                                      | PES46% PAN27% CO27%             |                    |
| WEIGHT (oz/yd2) / PESO (gr/m2) (+/-5%)                                         | 8.54 / 290                      |                    |
| WEIGHT (oz/yd) / PESO (gr/ml)                                                  | 26.19 - 13.09 / 812.00 - 406.00 |                    |
| ABRASION RESISTANCE (CYCLES) / RESISTENCIA A LA ABRASIÓN ( ciclos )            | 15000                           | UNE EN ISO 12947-2 |
| PILLING RESISTANCE ( degrees ) (1-5) / RESISTENCIA AL PILLING ( grados ) (1-5) | 4-5                             | UNE EN ISO 12945-2 |
| COLOUR FASTNESS TO LIGHT ( degrees ) (1-8) / SOLIDEZ A LA LUZ ( grados ) (1-8) | 5                               | UNE EN ISO 105-B02 |
| COLOUR FASTNESS TO RUBBING ( degrees ) (1-5) / SOLIDEZ AL FROTE ( grados )     | 5                               | UNE EN ISO 105-X12 |
| COLOUR FASTNESS TO WASH ( degrees ) (1-5) / SOLIDEZ AL LAVADO ( grados )       | 5                               | UNE EN ISO 105-C06 |
| (%) WARP SHRINKAGE / ENCOGIMIENTO URDIMBRE ( % )                               | 2.5                             | UNE EN ISO 5077.   |
| (%) WEFT SHRINKAGE / ENCOGIMIENTO TRAMA ( % )                                  | 4.2                             | UNE EN ISO 5077    |
| WARP TENSILE STRENGTH (N) / RESISTENCIA A LA TRACCIÓN URDIMBRE (N)             | 1080.42                         | UNE EN ISO 13934-1 |
| WEFT TENSILE STRENGTH (N) / RESISTENCIA A LA TRACCIÓN TRAMA (N)                | 425.54                          | UNE EN ISO 13934-1 |
| WARP EXTENSION AT BREAK (mm) / ALARGAMIENTO HASTA LA ROTURA                    | 45.05                           | UNE EN ISO 13934-1 |
| WEFT EXTENSION AT BREAK (mm) / ALARGAMIENTO HASTA LA ROTURA TRAMA              | 24.55                           | UNE EN ISO 13934-1 |
| WARP SEAM SLIPPAGE (mm) / DESLIZAMIENTO DE LA COSTURA URDIMBRE (mm)            | 4.5                             | UNE EN ISO 13936-1 |
| WEFT SEAM SLIPPAGE (mm) / DESLIZAMIENTO DE LA COSTURA TRAMA ( mm )             | 3.7                             | UNE EN ISO 13936-1 |
| FIRE RETARDANT RULE / IGNÍFUGOS UNE EN 1021:2014-1                             | PASA                            | UNE EN 1021:2014-1 |
| FIRE RETARDANT RULE / IGNÍFUGOS BS 5852-1                                      | PASA                            | BS 5852-1          |