











**FIRE  
RETARDANT**  
EN 1021-1:2014  
NFP A 260  
CAL TB 117  
BS 5852-1



27 inch. simulation  
70 cm. simulaci3n

## TECHNICAL SHEET / CARACTERÍSTICAS TÉCNICAS

|                                                                                |                                 |                    |
|--------------------------------------------------------------------------------|---------------------------------|--------------------|
| WIDTH (inches) / ANCHO (cm)                                                    | 55 - 110 / 140 - 280            |                    |
| HS CODE / PARTIDA ARANCELARIA                                                  | 52115100                        |                    |
| ROLL LENGTH (yd) / TAMAÑO PIEZA (mts)                                          | 27.5 / 25                       |                    |
| COMPOSITION / COMPOSICION                                                      | PES55% CO45%                    |                    |
| WEIGHT (oz/yd2) / PESO (gr/m2) (+-5%)                                          | 9.12 / 310                      |                    |
| WEIGHT (oz/yd) / PESO (gr/ml)                                                  | 14.00 - 27.99 / 434.00 - 868.00 |                    |
| ABRASION RESISTANCE (CYCLES) / RESISTENCIA A LA ABRASIÓN ( ciclos )            | >40000                          | UNE EN ISO 12947-2 |
| PILLING RESISTANCE ( degrees ) (1-5) / RESISTENCIA AL PILLING ( grados ) (1-5) | 5                               | UNE EN ISO 12945-2 |
| COLOUR FASTNESS TO LIGHT ( degrees ) (1-8) / SOLIDEZ A LA LUZ ( grados ) (1-8) | 5                               | UNE EN ISO 105-B02 |
| COLOUR FASTNESS TO RUBBING ( degrees ) (1-5) / SOLIDEZ AL FROTE ( grados )     | 5                               | UNE EN ISO 105-X12 |
| COLOUR FASTNESS TO WASH ( degrees ) (1-5) / SOLIDEZ AL LAVADO ( grados )       | 5                               | UNE EN ISO 105-C06 |
| (%) WARP SHRINKAGE / ENCOGIMIENTO URDIMBRE ( % )                               | 2                               | UNE EN ISO 5077.   |
| (%) WEFT SHRINKAGE / ENCOGIMIENTO TRAMA (%)                                    | 3                               | UNE EN ISO 5077    |
| WARP TENSILE STRENGTH (N) / RESISTENCIA A LA TRACCIÓN URDIMBRE (N)             | 1500                            | UNE EN ISO 13934-1 |
| WEFT TENSILE STRENGTH (N) / RESISTENCIA A LA TRACCIÓN TRAMA (N)                | 541.39                          | UNE EN ISO 13934-1 |
| WARP EXTENSION AT BREAK (mm) / ALARGAMIENTO HASTA LA ROTURA                    | 68.9                            | UNE EN ISO 13934-1 |
| WEFT EXTENSION AT BREAK (mm) / ALARGAMIENTO HASTA LA ROTURA TRAMA              | 22.3                            | UNE EN ISO 13934-1 |
| WARP TEARING STRENGTH ( N ) / RESISTENCIA AL RASGADO URDIMBRE ( N )            | >150                            | UNE EN ISO 13937-3 |
| WEFT TEARING STRENGTH (N) / RESISTENCIA AL RASGADO TRAMA (N)                   | 105.09                          | UNE EN ISO 13937-3 |
| WARP SEAM SLIPPAGE (mm) / DESLIZAMIENTO DE LA COSTURA URDIMBRE (mm)            | 2.9                             | UNE EN ISO 13936-1 |
| WEFT SEAM SLIPPAGE (mm) / DESLIZAMIENTO DE LA COSTURA TRAMA ( mm )             | 3.6                             | UNE EN ISO 13936-1 |
| FIRE RETARDANT RULE / IGNÍFUGOS UNE EN 1021:2014-1                             | PASA                            | UNE EN 1021:2014-1 |
| FIRE RETARDANT RULE / IGNÍFUGOS BS 5852-1                                      | PASA                            | BS 5852-1          |