



REPEAT WEFT REPETICIÓN TRAMA:  
REPEAT WARP REPETICIÓN URDIMBRE:

## BENGALA 59

### BENGALA 1.40 POLIPIEL COL.59



\* **SPECIAL MAINTENANCE / MANTENIMIENTO ESPECIAL** = / NO UTILIZAR DISOLVENTE

## TECHNICAL SHEET / CARACTERÍSTICAS TÉCNICAS

|                                                                                |                              |                    |
|--------------------------------------------------------------------------------|------------------------------|--------------------|
| WIDTH (inches) / ANCHO (cm)                                                    | 55 / 140                     |                    |
| HS CODE / PARTIDA ARANCELARIA                                                  | 39211200                     |                    |
| ROLL LENGTH (yd) / TAMAÑO PIEZA (mts)                                          | 33.0 / 30                    |                    |
| COMPOSITION / COMPOSICION                                                      | PVC84% PES12%<br>RESINAPAN4% |                    |
| WEIGHT (oz/yd2) / PESO (gr/m2) (+/-5%)                                         | 17.07 / 580                  |                    |
| WEIGHT (oz/yd) / PESO (gr/ml)                                                  | 26.19 / 812.00               |                    |
| ABRASION RESISTANCE (CYCLES) / RESISTENCIA A LA ABRASIÓN ( ciclos )            | >45000                       | UNE EN ISO 12947-2 |
| PILLING RESISTANCE ( degrees ) (1-5) / RESISTENCIA AL PILLING ( grados ) (1-5) | 5                            | UNE EN ISO 12945-2 |
| COLOUR FASTNESS TO LIGHT ( degrees ) (1-8) / SOLIDEZ A LA LUZ ( grados ) (1-8) | 6-7                          | UNE EN ISO 105-B02 |
| COLOUR FASTNESS TO RUBBING ( degrees ) (1-5) / SOLIDEZ AL FROTE ( grados )     | 5                            | UNE EN ISO 105-X12 |
| WARP TENSILE STRENGTH (N) / RESISTENCIA A LA TRACCIÓN URDIMBRE (N)             | 360                          | UNE EN ISO 13934-1 |
| WEFT TENSILE STRENGTH (N) / RESISTENCIA A LA TRACCIÓN TRAMA (N)                | 150                          | UNE EN ISO 13934-1 |
| WARP TEARING STRENGTH ( N ) / RESISTENCIA AL RASGADO URDIMBRE ( N )            | 23                           | UNE EN ISO 13937-3 |
| WEFT TEARING STRENGTH (N) / RESISTENCIA AL RASGADO TRAMA (N)                   | 26                           | UNE EN ISO 13937-3 |
| FIRE RETARDANT RULE / IGNÍFUGOS UNE EN 1021:2014-1                             | PASA                         | UNE EN 1021:2014-1 |
| FIRE RETARDANT RULE / IGNÍFUGOS BS 5852-1                                      | PASA                         | BS 5852-1          |