




# VELETA 61

VELETA 2.80 MONTBLANC 61



REPEAT WEFT REPETICIÓN TRAMA: 15 inches - 38 cm  
REPEAT WARP REPETICIÓN URDIMBRE: 14 inches - 35 cm

## TECHNICAL SHEET / CARACTERÍSTICAS TÉCNICAS

|                                                                                |                |                    |
|--------------------------------------------------------------------------------|----------------|--------------------|
| WIDTH (inches) / ANCHO (cm)                                                    | 110 / 280      |                    |
| HS CODE / PARTIDA ARANCELARIA                                                  | 54075300       |                    |
| ROLL LENGTH (yd) / TAMAÑO PIEZA (mts)                                          | 33.0 / 30      |                    |
| COMPOSITION / COMPOSICION                                                      | PES 100%       |                    |
| WEIGHT (oz/yd2) / PESO (gr/m2) (+/-5%)                                         | 9.12 / 310     |                    |
| WEIGHT (oz/yd) / PESO (gr/ml)                                                  | 29.48 / 914.00 |                    |
| ABRASION RESISTANCE (CYCLES) / RESISTENCIA A LA ABRASIÓN ( ciclos )            | 18000          | UNE EN ISO 12947-2 |
| PILLING RESISTANCE ( degrees ) (1-5) / RESISTENCIA AL PILLING ( grados ) (1-5) | 5              | UNE EN ISO 12945-2 |
| VELCRO EFFECT (1-5) / EFECTO VELCRO (1-5)                                      | 5              | CS4946             |
| COLOUR FASTNESS TO LIGHT ( degrees ) (1-8) / SOLIDEZ A LA LUZ ( grados ) (1-8) | 5              | UNE EN ISO 105-B02 |
| COLOUR FASTNESS TO RUBBING ( degrees ) (1-5) / SOLIDEZ AL FROTE ( grados )     | 5              | UNE EN ISO 105-X12 |
| COLOUR FASTNESS TO WASH ( degrees ) (1-5) / SOLIDEZ AL LAVADO ( grados )       | 5              | UNE EN ISO 105-C06 |
| (%) WARP SHRINKAGE / ENCOGIMIENTO URDIMBRE ( % )                               | 1              | UNE EN ISO 5077.   |
| (%) WEFT SHRINKAGE / ENCOGIMIENTO TRAMA ( % )                                  | 0.5            | UNE EN ISO 5077    |
| WARP TENSILE STRENGTH (N) / RESISTENCIA A LA TRACCIÓN URDIMBRE (N)             | 1470           | UNE EN ISO 13934-1 |
| WEFT TENSILE STRENGTH (N) / RESISTENCIA A LA TRACCIÓN TRAMA (N)                | 1500           | UNE EN ISO 13934-1 |
| WARP EXTENSION AT BREAK (mm) / ALARGAMIENTO HASTA LA ROTURA                    | 75             | UNE EN ISO 13934-1 |
| WEFT EXTENSION AT BREAK (mm) / ALARGAMIENTO HASTA LA ROTURA TRAMA              | 42             | UNE EN ISO 13934-1 |
| WARP TEARING STRENGTH ( N ) / RESISTENCIA AL RASGADO URDIMBRE ( N )            | 95             | UNE EN ISO 13937-3 |
| WEFT TEARING STRENGTH (N) / RESISTENCIA AL RASGADO TRAMA (N)                   | 145            | UNE EN ISO 13937-3 |
| WARP SEAM SLIPPAGE (mm) / DESLIZAMIENTO DE LA COSTURA URDIMBRE (mm)            | 1              | UNE EN ISO 13936-1 |
| WEFT SEAM SLIPPAGE (mm) / DESLIZAMIENTO DE LA COSTURA TRAMA ( mm )             | 1.6            | UNE EN ISO 13936-1 |
| FIRE RETARDANT RULE / IGNÍFUGOS UNE EN 1021:2014-1                             | PASA           | UNE EN 1021:2014-1 |
| FIRE RETARDANT RULE / IGNÍFUGOS BS 5852-1                                      | PASA           | BS 5852-1          |